

SealPot SP4017

Silicone Potting Firm Gel

Typical Properties			
Property	Unit	Value	Test Method
Color / Component		Opaque	Visual
Density (as mixed)	Gram /cc	1.01	ASTM D792
Viscosity at 25°C (as mixed)	cP.s	15,000	ASTM D2196
Property as Cured			
Color		Opaque	Visual
Hardness	Shore A	42	ASTM D2240
Dielectric Constant	@100Hz	2.60	ASTM D150
Dielectric Constant	@100 KHz	2.66	ASTM D150
Dissipation Factor	@100 Hz	< 0.003	ASTM D150
Dissipation Factor	@100 KHz	< 0.001	ASTM D150
Dielectric Strength	Volt/mil AC	> 400	ASTM D149
Volume Resistivity	Ohm-cm	> 10E+14	ASTM D257
Coefficient of Thermal Expansion	ppm/°C	< 300	IPC-TM-650
Tg	°C	-120	TGA
Useful Temperature Range	°C	-55 to 200	TGA
Shelf Life	Month	3@ < 5°C	Viscosity double
Cure Profile			
Cure at 125°C	Minutes	60	Durometer
Cure at 150°C	Minutes	30	Durometer
Weight loss in cure	Weight %	< 0.5%	TGA

These figures are only intended as a guide and should not be used in preparing specifications.

Characteristics

SealPot SP4017 is a one-part firm potting gel. It is a thixotropic (non-sag), addition-curing, silicone that cures at elevated temperature to a very firm rubbery gel with excellent adhesion to various plastics and metals. It is non-corrosive and self-priming adhesion, and can be automated to dispense from pails or hand extruded from cartridge.

Special Features and Benefits

- Very soft for stress compliance
- Excellent dielectric properties
- Mechanical shock and vibration damping
- Low bleeding, low volatile
- Broad range of temperature stability

Typical Applications

- Pot / encapsulate parts and cavities
- Seal lids, covers, housings, connectors
- Coat various electronic parts
- Automotive electronics
- Semiconductor and Telecommunications
- Vibration dampening
- Thermal stress coupling

For the flowable version of this potting gel, please select the United Adhesives' product SealPot SP4011.

Processing Instruction

Important! SealPot SP4017 is platinum cure system. Please keep applied surface / housing clean and avoid using this material on any place that contains sulfur, amine, phosphorous, organo-metals, acid, etc. because these contaminants could inhibit the cure the material.

We recommend running preliminary tests to optimize conditions for the particular application. Comprehensive processing instructions can be obtained by contacting directly to United Adhesives Inc.

Storage

SealPot SP4017 has a shelf life of at least 3 months when stored at < 5°C in the originally sealed container. Storage beyond the date specified does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety information

SealPot SP4017 silicone contains neither toxic nor corrosive substances that might require special handling precautions. General hygiene regulations should be observed. Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from United Adhesives Inc.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose. For technical, quality, or product safety questions, please contact directly to United Adhesives Inc.