

# ThermoFill TF2619

## High Thermally Conductive Interface Filling Material

Typical Properties			
Property	Unit	Value	Test Method
Color / Component		White / Grey	Visual
Density	Gram /cc	2.9	ASTM D792
Viscosity at 25°C	Pa.s	260	ASTM D2196
Property as Cured			
Color		White / Grey	Visual
Hardness	Shore OO	40	ASTM D2240
Thermal Conductivity	W/m-K	2.0	ASTM D5470
Heat Capacity at 25°C	J/g-K	1.0	ASTM D1269
Dielectric Constant	@1000Hz	4	ASTM D150
Dielectric Strength	Volt/mil AC	> 400	ASTM D149
Volume Resistivity	Ohm-cm	> 10E+14	ASTM D257
Coefficient of Thermal Expansion	ppm/C	140	IPC-TM-650
Temperature Usage	Degree °C	-80 to 200	TGA
Cure Profile			
Cure at 125°C	Min	60	DSC
Cure at 150°C	Min	30	DSC
Cure out gassing	Weight %	< 0.1%	TGA
Shelf Life at 25°C	Day	15	Viscosity double

These figures are only intended as a guide and should not be used in preparing specifications.

### Processing Instruction

**Important!** ThermoFill TF2619 is platinum cure system. Please keep applied surface clean and avoid using this material on any surface that contains sulfur, amine, phosphorous, organo-metals, acid, etc. because these contaminants could inhibit the cure of the material.

For the package in a container (not in a cartridge), to ensure homogeneity of the material, the components must be stirred thoroughly before they are removed or processed in order to uniformly disperse any fillers that might have settled during storage.

We recommend running preliminary tests to optimize conditions for the particular application. Comprehensive processing instructions can be obtained by contacting directly to United Adhesives Inc.

### Storage

ThermoFill TF2619 has a shelf life of at least 6 months when stored between 5°C and 30 °C in the originally sealed container. The 'Best use before end' date of each batch appears on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

### Safety information

Addition curing ThermoFill TF2619 silicone gel contains neither toxic nor corrosive substances that might require special handling precautions. General hygiene regulations should be observed. Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from United Adhesives Inc.

### Characteristics

ThermoFill TF2619 is a high thermally conductive interface gap filling material. It is a non-slump, addition-curing, one-component silicone that cures at room temperature or elevated temperature to a very soft rubber with excellent thermal conductivity. The cured material provides Very low thermal stress for thermal cycles. TF2619 is dispensable and printable.

### Special Features and Benefits

- High thermal conductivity
- Almost constant properties from -70 to 180 °C
- Very low modulus for stress compliance
- Low bleeding, low volatile
- Pre-added 7 mil glass bead for thickness control (Average distance between beads is ~34 mil)

### Typical Applications

- Automotive electronics
- Semiconductor and Telecommunications
- Between high heat power device and heat sink
- Thermally conductive vibration dampening
- Couple thermal stress while dissipating heat

ThermoFill TF2619 has a shelf life of at least 6 months when stored < 5 °C in the originally sealed container. After cure it forms a low modulus "gel-like" material that is not for structure bonding purpose.